



## SMAART MATT CLEAR

### PRODUCT DESCRIPTION

SMAART 2K PU MATT CLEAR is a two component acrylic - based clearcoat. It is a high performance 2K clear coat, designed specifically to achieve a matt finish. It is characterized by excellent flow, high chemical resistance and hardness properties.


### FEATURES

- It is appropriate to finish matt, satin matt and satin gloss metallic and effect coatings.
- For use on plastic parts (e.g.bumpers) just add the additive Plastic Adhesion Promoter. Scratch Resistant.
- It is also suitable for spot, panel and overall repairs

### SURFACE PREPARATION

Must be applied on top of a clean, dry, dust free base coat surface (use of tack cloth is suggested to remove dirt & dust particles from the base coat surface before clear coat application.)

### APPLICATION METHOD



Application Method	Pressure/bar	Nozzle/mm	Spray Passes	Thinner (%)
Gravity spray gun (high pressure)	2.5 - 3	1.3 -1.4	2 - 2.5	0 - 25
HVLP (low pressure)	2.5 - 3	1.3 -1.4	2 - 2.5	0 - 25

**SMAART MATT CLEAR**



**Pot life:**  
4 hrs with Smaart Standard Hardener @ 30°C



**Hardener:**  
Smaart PU Standard Hardener



**Thinner:**  
Smaart Standard PU Thinner








**Drying Time:**

Object temperature	Dust Dry/min	Set to touch	Ready for assembly	Sandable	Recoatable
30°C	10- 15min	20- 30 min	4 h	24 h	NA
60°C	NA	30 min	2 h	NA	NA

## SMAART MATT CLEAR

### TECHNICAL INFORMATION

	Colour : Colourless
	Mixing Ratio : 4 : 1 (by volume) (4 parts of Clear & 1 part of Hardener)
	Spraying Viscosity : 18 - 20 s FORD CUP #4
	Flash Off Time : 10 - 15 min. before oven drying
	Dry Coat Thickness : 40 - 50 $\mu\text{m}$

**Approx Coverage: 7 - 8 m<sup>2</sup>/l (for 40 - 50  $\mu\text{m}$  DFT )**

Storage :	1 year from the date of manufacturing at 30° C, if stored in a dark / dry place in a tightly closed container.
VOC Regulation :	This product contains max. 474 g/l of VOC.
Processing Conditions :	From +10°C and up to 80% relative air humidity. Ensure an adequate air ventilation.

This data sheet is for information purpose only. To our knowledge the data provided complies with the latest standard and is based on years of experience in the manufacture of our products. However the data is not binding and without warranty. Please follow recommendations stated on the relevant precautions stated on the product label. We reserve our right to make additions, deletions or modifications to the information at any time without prior notification.