



SMAART 7077 HS CLEAR

PRODUCT DESCRIPTION

SMAART 7077 HS Clearcoat is two pack material, designed to give excellent gloss and sharp image clarity through easy application, good flow and build. Excellent abrasion and impact resistance. Suitable for high quality multiple coat system.


FEATURES

- It is a High-Solid acrylic clearcoat for complete or partial paintwork of cars and commercial vehicles.
- It can be polished after forced drying.
- It is highly resistant to all kind of weathering as well as to mechanical stress and chemical agents.
- It has excellent drying properties especially in case of oven drying.
- It guarantees an optimal curing especially in case of oven drying but also at room temperature

SURFACE PREPARATION

Must be applied on top of a clean, dry, dust free base coat surface (use of tack cloth is suggested to remove dirt & dust particles from the base coat surface before clear coat application.)

APPLICATION METHOD



Application Method	Pressure/bar	Nozzle/mm	Spray Passes	Thinner (%)
Gravity spray gun (high pressure)	2.5 - 3	1.3 -1.4	2 - 2.5	0 - 25
HVLP (low pressure)	2.5 - 3	1.3 -1.4	2 - 2.5	0 - 25

SMAART 7077 HS CLEAR



Pot life:
1.5 hrs with Smart PU Standard Hardener @ 30°C



Hardener:
Smart PU Standard Hardener



Thinner:
Smart Standard PU Thinner








Drying Time:

Object temperature	Dust Dry/min	Set to touch	Ready for assembly	Sandable	Recoatable
30°C	10 - 15 min	25 - 35 min	6 h	NA	NA
60°C	NA	30 min	2 h	NA	NA

SMAART 7077 HS CLEAR

TECHNICAL INFORMATION

	Colour : Colourless
	Mixing Ratio : 2 : 1 (by volume) (2 parts of Clear & 1 part of Hardener)
	Spraying Viscosity : 18 - 20 s FORD CUP #4
	Flash Off Time : 10 - 15 min. before oven drying
	Dry Coat Thickness : 50- 60 μm

Approx Coverage: 8 - 10 m²/l (for 50 - 60 μm DFT)

Storage :	1 year from the date of manufacturing at 30° C, if stored in a dark / dry place in a tightly closed container.
VOC Regulation :	EU limit value for this product (category B/c): 420 g/l This product contains max. 420 g/l of VOC.
Processing Conditions :	From +10°C and up to 80% relative air humidity. Ensure an adequate air ventilation.

This data sheet is for information purpose only. To our knowledge the data provided complies with the latest standard and is based on years of experience in the manufacture of our products. However the data is not binding and without warranty. Please follow recommendations stated on the relevant precautions stated on the product label. We reserve our right to make additions, deletions or modifications to the information at any time without prior notification.