

SMAART DYNAMIC CLEAR COMBI PACK (4:1)

PRODUCT DESCRIPTION

SMAART DYNAMIC CLEAR 4:1 is High gloss finish and suitable for multiple coat systems. Completely cured film is tough and flexible, weather, chemical, abrasion and impact resistant, good gloss retention even under severe weather conditions.


FEATURES

- It is a High-Gloss acrylic clearcoat for complete or spot repair paintwork in Auto refinish Coating
- It can be polished and good sandability
- It is highly resistant to all kind of weathering as well as to mechanical stress and chemical agents
- It has excellent drying properties

SURFACE PREPARATION

Must be applied on top of a clean, dry, dust free base coat surface (use of tack cloth is suggested to remove dirt & dust particles from the base coat surface before clear coat application.)

APPLICATION METHOD



Application Method	Pressure/bar	Nozzle/mm	Spray Passes	Thinner (%)
Gravity spray gun (high pressure)	2.5 - 3	1.3 -1.4	2 - 2.5	0 - 25
HVLP (low pressure)	2.5 - 3	1.3 -1.4	2 - 2.5	0 - 25

SMAART DYNAMIC CLEAR COMBI PACK (4:1)



Pot life:
3 hrs with Smart Standard Hardener @ 30°C



Hardener:
Smart PU Standard Hardener



Thinner:
Smart Standard PU Thinner








Drying Time:

Object temperature	Dust Dry/min	Set to touch	Ready for assembly	Sandable	Recoatable
30°C	15- 20 min	30- 50 min	4 h	24 h	NA
60°C	NA	30 min	2 h	NA	NA

SMAART DYNAMIC CLEA COMBI PACK (4:1)

TECHNICAL INFORMATION

	Colour : Colourless
	Mixing Ratio : 4 : 1 (by volume) (4 parts of Clear & 1 part of Hardener)
	Spraying Viscosity : 18 - 20 s FORD CUP #4
	Flash Off Time : 10 - 15 min. before oven drying
	Dry Coat Thickness : 40 - 50 μm

Approx Coverage: 7 - 8 m²/l (for 40 - 50 μm DFT)

Storage :	1 year from the date of manufacturing at 30° C, if stored in a dark / dry place in a tightly closed container.
VOC Regulation :	This product contains max. 474 g/l of VOC.
Processing Conditions :	From +10°C and up to 80% relative air humidity. Ensure an adequate air ventilation.

This data sheet is for information purpose only. To our knowledge the data provided complies with the latest standard and is based on years of experience in the manufacture of our products. However the data is not binding and without warranty. Please follow recommendations stated on the relevant precautions stated on the product label. We reserve our right to make additions, deletions or modifications to the information at any time without prior notification.